## Labshop Chemicals Restoration Art Supplies

### K4806 Iron Oxide Yellow 960, light

### **Product Information**

Type:	Yellow pigment	
Delivery form:	Powder	
Chemical class:	Synthetic iron oxide $\alpha$ -FeOOH	
Color Index:	Pigment Yellow 42 (77492)	
	Pigment Red 101 (77491)	
CAS-No.:	51274-00-1 + 1309-37-1	

### Specification

Color values and tinting strength

	min.	max.	Test method
Binder: test paste based on a	<u>111111.</u>	<u>max.</u>	rest method
non drying alkyd resin			
Full shade			No. 001 of 1995-04-28
$\Delta L^*$	-0.3	0.5	10.001011))5-04-20
$\Delta a^*$	-1.0	1.0	
$\Delta b^*$	-1.3	1.3	
$\Delta E_{ab}$ *		1.5	
Reduced shade with titanium dioxide (1:5)			
Reduced shade with trainfull dioxide (1.5)			
Aa*	-1.0	1.0	
	-1.0 -1.3	1.0 1.3	
$\Delta a^*$ $\Delta b^*$			
$\Delta a^*$		1.3	No. 001 of 1995-04-28
$\Delta a^*$ $\Delta b^*$ $\Delta E_{ab}^*$ Relative tinting strength (%)	-1.3	1.3 1.5	No. 001 of 1995-04-28
$\Delta a^*$ $\Delta b^*$ $\Delta E_{ab}^*$	-1.3	1.3 1.5	No. 001 of 1995-04-28 No. 004 of 1995-05-15

# Labshop

### **Technical Data:**

	<u>min.</u>	<u>max.</u>	Test method
Water-soluble content (%)		0.5	DIN EN ISO 787 part 3 (1995)
Sieve residue (0.045-mm-sieve) (%)		0.05	DIN 53 195 (1990)
pH-value	3.5	7.5	DIN EN ISO 787 part 9 (1995)

### Informative technical data (standard values)

Content Fe2O3 Content SiO <sub>2</sub> + Al <sub>2</sub> O <sub>3</sub> Loss on ignition at 1000°C, 0.5h	88 % 3.0 % 11 %	<u>Test method</u> DIN 55 913 sheet 2 (1972) DIN 55 913 sheet 2 (1972) DIN 55 913 sheet 2 (1972)
Moisture content (after production)	< 0.5 %	DIN EN ISO 787 Part 2 (1995)
Particle size	spicular	
Predominant particle size	0.1 x 0.6 μm	Electron microscope
Oil absorption (g/100 g)	$40 \pm 10$	DIN EN ISO 787 part 5 (1995)
Tamped density (g/ml)	0.4 - 0.8	DIN EN ISO 787 part 11 (1995)
Density (g/ml)	4.5	DIN EN ISO 787 part 10 (1995)

#### **Transport and storage**

Protect against weathering. Store in a dry place and avoid extreme fluctuations in temperature. Special conditions for opened packaging: Close bags after use to prevent the absorption of moisture and contamination.

#### Safety

The product is not classified as dangerous under the relevant EC Directives and corresponding national regulations valid in the individual EU member states. It is not dangerous according to transport regulations. In countries outside the EU, compliance with the respective national legislation concerning the classification, packaging, labelling and transport of dangerous substances must be ensured.

The information contained in the safety data sheet must be observed. This contains information on handling, product safety and ecology.

This product meets the requirements of the European Toys Regulation DIN EN 71, part 3.