

## **O713 Polyglykol 1000**

### **Product Specification**

<b>Item</b>	<b>Specification</b>	<b>Unit</b>	<b>Method</b>
Consistence at 20°C visual	wax-like		
Hazen color 25% a.i. in water	max. 30		EN 1557
Solubility 25% a.i. in water visual	clear		
Viscosity at 20°C of 50% solution	24 - 28	mPa·s	DIN 51562
pH Value 5% in water	5.0 – 7.5		DIN EN 1262
Water content Karl-Fischer	max. 0.50	%	DIN 51777
Ethylene oxide	max. 1	ppm	Head-Space GC
Dioxane content (calculated at 100 %)	max. 1	ppm	Head-Space GC
OH value	107 - 118	mg KOH/g	DIN EN ISO 4629
Molar mass (calculated) of OH value	950 - 1050	g/mol	