

# HXTAL NYL-1

## HXTAL NYL-1 TECHNICAL SHEET

Developed specifically for the conservation and restoration industries, HXTAL NYL-1 is a two part, low viscosity epoxy with exceptional non-yellowing properties combined with high strength characteristics.

HXTAL NYL-1 is a hard, water white epoxy that bonds to glass, ceramic, metals, wood, ivory, marble and many other substrates.

For best results, HXTAL NYL-1 should be accurately mixed by weight 3 parts of A (resin) to 1 part B (hardener).

HXTAL reaches 90% bond cure in 7 days at room temperature (roughly 75°F, 24°C).



### TECHNICAL DATA

#### PHYSICAL PROPERTIES

Appearance	Colorless, clear two part epoxy
Tensile Strength	5400psi
Tensile Modulus	316,000 psi
Elongation	3%
Flexural Strength	10,100 psi
Flexural Modulus	365,000 psi
Impact Strength	0.14 ft lbs/inch
Heat Distortion Temp 264/66psi	37.5°C/39°C
Hardness (Shore D) 0/10secs	78/73
Refractive Index	1.515
Gel time, 110g mass 150°F 100°F	25.8 minutes 262.7 minutes
Cure of 0.2mm film at 25°C Cure to touch Full Cure	15.3 hours 30.9 hours
Initial Yellowness index	~6
Yellowness after 1600 hours of weatherometer exposure	~6-8
Yellowness after 3000 hours of weatherometer exposure	~13

The information in this technical data sheet is considered accurate at the time of publication. No warranty to usage is expressed or implied by this data. Individual usage may vary and results of usage may vary from these details and HXTAL Adhesive, LLC is not held liable for any information expressed herein.

**HXTAL Adhesive, LLC**  
www.hxtal.com

Distributor: **Interlabshop BV**