

O59825 Glass Powder, very fine

Chemical Composition

SiO ₂	77 - 80 %
B ₂ O ₃	9 - 13 %
Al ₂ O ₃	2 - 4 %
Na ₂ O	4 - 5 %
K ₂ O	1 %
ZrO ₂	0 - 1 %

Physical Data

Moisture:	≤ 0.5 %
Density:	2.25 g/cm ³
Refractive index:	1.47
Oil absorption:	32 ml / 100 g
Conductivity:	134 μS/cm

Max. Application temperature:	ca. 500°C
Transformation temperature:	ca. 550°C
Sintering point:	ca. 700°C
Softening point:	ca. 1180°C
Flow point:	ca. 1300°C

Particle Size

Alpine air jet sieve (200LS-N) < 20 μm	< 5 %
---	-------

CILAS 920 Laser Granulometer

D90	30 μm
D50	10 μm
D10	1.5 μm